

gipgum

Two-component sealant
for waterproofing terraces,
balconies, water tanks,
and shower cubicles

A+B



TECHNICAL MORTARS



Gipgum A+B

Two-component sealant for waterproofing terraces, balconies, water tanks, and shower cubicles

TECHNICAL FEATURES



Theoretical yield	~ 1,7 Kg/m ² for 1 mm thick
Granulometry	≤ 0,5 mm
Mixture volumetric mass	1,7 Kg/lt
Mixing ratio (dust/latex)	3:1
Mixture life time	~ 60 min
Walkability	24/48 hours
Waiting for ceramic laying	7 days
Adhesion to concrete	≥ 1 N/mm ²
Recommended application thickness	3-5 mm

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

Pour component B into a clean container and slowly mix in component A to obtain a smooth blend free of lumps. Apply the first coat with a toothed spatula in a continuous action. Lay the fibreglass reinforcement mesh and smooth in so that it incorporates into the previous layer. After 6 to 8 hours, when hardened, apply a second coat working crosswise to the previous coat.



WARNINGS

Do not add additives or aggregates of any kind.
Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.
Do not apply at temperatures below + 5 ° C or above + 35 ° C.
Do not apply on wooden or metal substrates not previously treated with Primer Gps.
Keep the product in the bags intact, on pallets and in a dry and ventilated place.



PACKAGING

Paper bags of kg. 24 + tank.

The above information is to be considered indicative, non-binding and subject to change without notice.
Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.