

# *brunelleschi*

## QUARTZ ACRYLIC PAINT

Micronized quartz paint based on acrylic binders indicated for finishing facades of new buildings or existing.


### Application



by brush



by roller



by spray

# Brunelleschi

Quartz acrylic paint



## TECHNICAL FEATURES

<b>Theoretical yield</b>	~ 0,300 Lt/m <sup>2</sup> two-hand
<b>Viscosity</b>	~ 37.000 mPa*s
<b>Specific weight</b>	~ 1,60 Kg\Lt
<b>PH</b>	> 9,50
<b>Colours</b>	Folder colors
<b>Classification by final use</b>	Decoration and protection

## CHARACTERISTICS OF INSTALLATION

<b>First hand dilution with water</b>	30%
<b>Second hand dilution with water</b>	20%
<b>Interval between 1<sup>st</sup> and 2<sup>nd</sup> hand</b>	at least 12 hours
<b>Dry to the touch</b>	~ 1 hour
<b>Deep dry</b>	~ 24 hours

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



## METHOD OF USE

The walls should be mature and dry, free from dust and dirt. Brush and dust any loose parts, oily residues, plant formations, saline efflorescence or processing residues. Treat with BRUNELLESCHI PRIMER ACRYLIC in advance surfaces that are particularly absorbent or have strong differences in absorption and plasters that are not very consistent and flaky. It can be applied by brush, roller or spray. The first coat should be diluted with 30% water, the second with 20%.



## WARNINGS

*The chromatic aspect may vary according to the absorption of the support and the climatic conditions.*

*Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.*

*Do not apply at temperatures below + 5 ° C or above + 35 ° C.*

*Do not apply in conditions of intense sun, high wind or possible rain.*

*Keep the product in the bags intact, on pallets and in a dry and ventilated place.*



## PACKAGING

Plastic tanks of Lt. 25

*The above information is to be considered indicative, non-binding and subject to change without notice.*

*Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.*