

# *palladio*

## SILOXANE PAINT

Siloxane paint based on colloids stabilized minerals, Indicated as finishing of new buildings and in the restoration of buildings historical or seaside resorts.


### Application



by brush



by roller



by spray

# Palladio

Siloxane Paint



## TECHNICAL FEATURES

|                                    |                                    |
|------------------------------------|------------------------------------|
| <b>Expected yield</b>              | ~ 0,550 Lt/m <sup>2</sup> two-hand |
| <b>Viscosity</b>                   | ~ 38.000 mPa*s                     |
| <b>Specific weight</b>             | ~ 1,60 Kg\Lt                       |
| <b>PH</b>                          | > 9,50                             |
| <b>Colours</b>                     | Folder colors                      |
| <b>Classification by final use</b> | Decoration and Protection          |

## CHARACTERISTICS OF INSTALLATION

|  |                   |
|--|-------------------|
| <b>First hand dilution with water</b>                          | 30%               |
| <b>Second hand dilution with water</b>                         | 20%               |
| <b>Interval between 1<sup>st</sup> and 2<sup>nd</sup> hand</b> | at least 12 hours |
| <b>Dry to the touch</b>  | ~ 1 hour          |
| <b>Deep dry</b>  | ~ 48 hours        |

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



## METHOD OF USE

The walls should be mature and dry, free from dust and dirt. Brush and dust any loose parts, oily residues, plant formations, saline efflorescence or processing residues. Treat with BRUNELLESCHI PRIMER ACRYLIC in advance surfaces that are particularly absorbent or have strong differences in absorption and plasters that are not very consistent and flaky. In the case of non-friable plasters or consistent smoothing it is sufficient to isolate with a layer of BRUNELLESCHI ACRYLIC QUARTZ PAINT. The application is done by laying with steel trowel and subsequent finishing with plastic trowel in one hand.



## WARNINGS

*The chromatic aspect may vary according to the absorption of the support and the climatic conditions.*  
*Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.*  
*Do not apply at temperatures below + 5 ° C or above + 35 ° C.*  
*Do not apply in conditions of intense sun, high wind or possible rain.*  
*Keep the product in the bags intact, on pallets and in a dry and ventilated place.*



## PACKAGING

Plastic tanks of Lt. 25

*The above information is to be considered indicative, non-binding and subject to change without notice.*  
*Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.*