

micchelangelo

IDROPITTURA DUCOTONE

Washable water-based paint for indoor and outdoor use, suitable for any support such as plaster based on cement and/or plaster, plasterboard and concrete.


Application



by brush



by roller



by spray

Michelangelo

Idropittura ducotone



TECHNICAL FEATURES

Expected yield	~ 0,180 Lt/m ² two-hand
Viscosity	~ 37.000 mPa*s
Specific weight	~ 1,50 Kg\Lt
PH	> 9,00
Covering power	96 < Valore Tristimolo Y < 98
Water absorption	0,1 < W < 0,3 Kg/(m ² xH ^{0.5})
Classification by final use	Decoration and Protection

CHARACTERISTICS OF INSTALLATION

First hand dilution with water	40%
Second hand dilution with water	30%
Interval between 1st and 2nd hand	about 10 hours
Dry to the touch	~ 1 hour
Deep dry	~ 48 hours

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

The walls should be mature and dry, free from dust and dirt. Any traces of oils, waxes, fats, etc. must be removed. Apply a primer to particularly absorbent surfaces and low-consistency, flaky plasters. Then apply two or more coats by roller, brush or spray. Dilute the first coat with 40 % water, the second with 30 %. In the case of walls treated with paints that are not firmly anchored, a pre-treatment of brushing, scraping and, if necessary, stripping of the parts to be removed is necessary.



WARNINGS

The chromatic aspect may vary according to the absorption of the support and the climatic conditions.

Do not apply on inconsistent, dusty or degraded, frozen or wet substrates.

Do not apply at temperatures below + 5 ° C or above + 35 ° C.

Do not apply in conditions of intense sun, high wind or possible rain.

Keep the product in the bags intact, on pallets and in a dry and ventilated place.



PACKAGING

Plastic tanks of Lt. 14

The above information is to be considered indicative, non-binding and subject to change without notice.

Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.