

gipAncoral

Promoter of adhesion of substrate plasters
on smooth or poorly absorbent substrates




TECHNICAL FEATURES



Theoretical yield	~ 200 g/m ² (diluted product)
Specific weight	1,5 Kg/lt
Granulometry	≤ 0,5 mm
pH	~ 8 (slightly alkaline)
Drying	12÷24 h (from the drafting)
Overlay	48 h (from the drying)
Color	white milk

Laboratory tests performed at + 20 ° C and R.H. 65%, data subject to variations in different atmospheric and installation conditions.



METHOD OF USE

Mix the product, by hand or with a low-speed drill, in clean water with a dilution ratio of the product + water from 1 ÷ 4 to 1 ÷ 6. Distribute evenly on the surface to be treated (smooth or unarmored concrete, splinters of tuff or stone, old plaster, etc.), using a soft bristle brush or a long-haired paint roller, stirring the diluted product after each stop.



WARNINGS

Keep the product in well-closed containers, in a dry, ventilated place and with an ambient temperature $\geq 5^{\circ}\text{C}$. Non-toxic product.

The above information is to be considered indicative, non-binding and subject to change without notice. Therefore the suitability of the product for the desired result must be verified by the user, who is fully responsible for its use.



PACKAGING

12 kg drum.

CHEMICAL ADDITIVES

